

U.S.S.N. 09/785,593

Filed: February 16, 2001

AMENDMENT AND RESPONSE TO OFFICE ACTION

---

**In the Claims**

1. (currently amended) A resorbable interbody spinal fusion device for spinal fixation, said device comprising an interbody spinal fusion device comprising between 25 and 100% polymer producing acidic products or low molecular weight resorbable fragments upon hydrolytic degradation, one or more void spaces, and a buffering or neutralizing agent, wherein one or more of the void spaces contains a grafting material for facilitating bony development and/or spinal fusion.

2. (canceled)

3. (canceled)

4. (currently amended) The resorbable interbody spinal fusion device of claim 1, wherein said grafting material is an autologous grafting material.

5. (withdrawn) The resorbable interbody spinal fusion device of claim 1, wherein said device is shaped substantially as a tapered wedge or cone.

6. (original) The resorbable interbody spinal fusion device of claim 1, wherein said device is shaped substantially as a threaded screw.

7. (withdrawn) The resorbable interbody spinal fusion device of claim 1, wherein said device is shaped substantially as a threaded rod of cruciform configuration.

8. (withdrawn) The resorbable interbody spinal fusion device of claim 5, further comprising at least one serrated or threaded outer face.

9. (canceled)

U.S.S.N. 09/785,593

Filed: February 16, 2001

## AMENDMENT AND RESPONSE TO OFFICE ACTION

10. (canceled)

11. (original) The resorbable interbody spinal fusion device of claim 1, wherein said resorbable material is a polymer selected from the group consisting of polydioxanone, poly(epsilon-caprolactone), polyanhydride, polyester, copoly(ether-ester), polyamide, polylactone, poly(propylene fumarate), and combinations thereof.

12. (original) The resorbable interbody spinal fusion device of claim 11, wherein said bioerodible polymer comprises poly(lactide-co-glycolide) with a lactide to glycolide ratio in the range of 0:100% to 100:0% inclusive.

13. (withdrawn) The resorbable interbody spinal fusion device of claim 10, wherein said buffering or neutralizing agent is a polymer comprising at least one basic group.

14. (withdrawn) The resorbable interbody spinal fusion device of claim 13, wherein said polymer comprising at least one basic group is selected from the group consisting of polyamines, polyesters, vinyl polymers, and copolymers of acrylic acid.

15. (withdrawn) The resorbable interbody spinal fusion device of claim 10, wherein said buffering or neutralizing agent is a compound that, on exposure to water, hydrolyzes to form a base.

16. (previously presented) The resorbable interbody spinal fusion device of claim 1, wherein said buffering or neutralizing agent is selected from the group consisting of carbonates, phosphates, acetates, succinates and citrates.

U.S.N. 09/785,593

Filed: February 16, 2001

## AMENDMENT AND RESPONSE TO OFFICE ACTION

17. (original) The resorbable interbody spinal fusion device of claim 1 wherein said resorbable material further comprises reinforcing fibers.

18. (original) The resorbable interbody spinal fusion device of claim 17, wherein said reinforcing fibers are made of said resorbable polymer.

19. (canceled)

20. (currently amended) The resorbable interbody spinal fusion device of claim 17 19, wherein said reinforcing fibers are made of said buffering or neutralizing agent.

21. (canceled).

22. (canceled).

23. (canceled).

24. (withdrawn) The resorbable interbody spinal fusion device of claim 10 wherein said buffering or neutralizing agent is selected from the group consisting of compounds wherein the pKa of the conjugate acids of said compounds is greater than the pKa of acids produced by hydrolysis of the polymer(s) from which said device is prepared.

25. (original) The resorbable interbody spinal fusion device of claim 1, wherein said device is fabricated from at least two resorbable polymers.

26. (original) The resorbable interbody spinal fusion device of claim 25, wherein one of said resorbable polymers is poly (propylene fumarate).

27. (original) The resorbable interbody spinal fusion device of claim 25, wherein one of said resorbable polymers has been cross-linked in the presence of a crosslinking agent and an

U.S.S.N. 09/785,593  
Filed: February 16, 2001  
AMENDMENT AND RESPONSE TO OFFICE ACTION

initiator, whereby said crosslinked resorbable polymer forms a reinforcing interpenetrating network.

28. (previously presented) The resorbable interbody spinal fusion device of claim 25, wherein one of said at least two resorbable polymers has been cross-linked in the presence of vinyl pyrrolidone as a crosslinking agent and an initiator.

29. (previously presented) The resorbable interbody spinal fusion device of claim 25, wherein one of said at least two resorbable polymers has been cross-linked in the presence of a crosslinking agent and benzoyl peroxide as an initiator.

30. (original) The resorbable interbody spinal fusion device of claim 1, wherein said device is fabricated from a polymer wherein molecular chains of said polymer have been aligned to be essentially parallel.

31. (original) The resorbable interbody spinal fusion device of claim 30, wherein said device has been cut such that the aligned polymer molecular chains are at approximately a 45° angle to a surface of said device.

32. (canceled)

33. (previously presented) The resorbable interbody spinal fusion device for spinal fixation of claim 1, wherein said buffering or neutralizing agent is hydroxyapatite.

34. (canceled)